IN THE CLAIMS:

Please replace the claims with the following:

- (Currently Amended) A method of manufacturing a polyethylene glycol treated fabric comprising:
- (a) exposing a fabric to a polyethylene glycol formulation including an acid catalyst and a resin to form a wet fabric:
- (b) heating and curing the wet fabric at a temperature such that the surface temperature of the wet fabric reaches a temperature sufficient to initiate a catalytic reaction for bonding the polyethylene glycol formulation to the fabric and in the heating and curing step the surface temperature does not exceed 220°F to form a treated fabric;
- (c) neutralizing the treated fabric to a pH between about 6.5 to about 7.5 to form a neutralized fabric; and
 - (d) drying the neutralized fabric.